



CICO SHOT P

Gunite & Shotcrete Accelerator

CICO SHOT P is a quick setting and waterproofing compound available in powder form for use with sprayed concrete or gunite.

USES

CICO SHOT- P is used for sprayed concrete and mortar in galleries and tunnels, for retaining walls, embankment and tank linings etc. **CICO SHOT- P** admixed mortar sets rapidly, hence, quick placing of the wet mortar is essential.

ADVANTAGES

- Allows spraying to take place even on wet surface subject to slight infiltration.
- Speeds the work and contributes to good water tightness of the sprayed concrete linings.
- Improves overhead spraying and reduces rebound.
- Does not contain any chlorides or nitrates and will not corrode.

PROPERTIES

Form	Powder
Colour	White
Chloride Content	Nil
Shelf Life	24 months

CONSISTENCY

CICO SHOT- P is formulated from carefully selected raw materials and is manufactured under control conditions to give a consistent product.

HANDLING

CICO SHOT- P is formulated from chemicals which present no fire or health hazards.

STORAGE

If stored in undamaged bags in dry condition at normal ambient temperatures, a shelf-life of 12 months can be expected. This product is insensitive to frost.

METHOD OF USE

The required amount of **CICO SHOT- P** is mixed with (dry sand - cement) or (gravel-sand-cement) mixture. Large quantities of dry mix can be prepared if protected against moisture and using dry sand. When guniting is interrupted care must be taken that water does not floor back in the supply hose causing the mix to set.

RATE OF ADDITION

The optimum dosage should be determined by site trials. As a guide the typical rate of addition and setting time is given below:

Dosage of CICO SHOT P	Initial Set	Final Set
1% - 2%	3'00" - 4'30"	10'00"- 12'00"
3% - 4%	1'00" - 1'30"	2'30"- 4'00"
5% - 7%	0'30" - 1'00"	1'00"- 2'00"

Note: The above results are based on Gilmore Test using Ordinary Portland Cement.



PACKING

CICO SHOT P is available in 25 kg Polythene Lines waterproof bags.

Important Note:

All CICO products are sold in the market after strict Quality Control in line of ISO 9001 and guaranteed against any manufacturing defect. Although the basic formulation of Company's products generally remains unchanged, production refinements arising from continuing research and evaluation program may occasionally result in marginal changes in properties. CICO aspires to ensure that any recommendation, advice, test data, specification, method statement and other information given in this product datasheet is accurate and best of company's knowledge. Since, the company (CICO TECHNOLOGIES LTD) has no control over the selection of its product, applicators, application methodology, how and where it is applied, therefore, the company cannot accept any liability directly or indirectly arising from the use of its product. It is important to any customer, user or specifier satisfies him / herself that the product is suitable for the intended purpose including health, safety and environmental aspect. Unless or otherwise agreed in writing, all products of the company are sold strictly pursuant to the terms of our standard conditions of sale which are available upon request. All information and technical assistance is given without warranty or guarantee and is subject to change without notice. All customers, users, specifiers should ensure that they examine the suitability of the product with company's latest product data sheet.

CICO TECHNOLOGIES LIMITED

Corp. Office: C-44/2, 1st & 2nd Floor, Okhla Industrial Area,
Phase -II, New Delhi-110 020

Tel. No: 91-11-4050 9400, Fax: 91-11-4050 9413

E-Mail: cicotech@cicogroup.com

Web Site: www.cicogroup.com



ISO 9001:2008
FM 54275

CTL/07-14/01