

Product Data Sheet
Edition 18/07/2007
Identification no:
02 02 01 01 001 0 000000
SikaGrout®-214

SikaGrout®-214

High precision, non shrink, expanding pouring grout

Product Description Cement based flowable, two stage expanding grout with selected aggregate.

Uses

- To grout bearings, machine foundations, columns joints in precast construction etc.
- To grout anchors in concrete
- To grout cavities, gaps and voids in concrete

Characteristics / Advantages

- Easy to use (ready to mix powder)
- Easy to mix, only add water
- Adjustable consistency
- Very good flow characteristics
- Rapid strength development
- High final strengths
- Initial expansion by gas generation
- Impact- and vibration resistant
- Non-corrosive
- Not flammable, non-toxic
- Shrinkage compensated

Product Data

Form

Appearance / Colour Grey powder

Packaging 25 kg bags

Storage

Storage Conditions / Shelf-Life 6 months from date of production if stored properly in dry conditions in undamaged and unopened original sealed packaging.

Construction



Technical Data

Chemical Base	Cement, selected fillers and aggregates, special additives	
Bulk Density	1.2 kg/l (of fresh grout) at 27 °C	
Grading	2.36 mm down	
Layer Thickness	SikaGrout®-214:	20 mm min. / 50 mm max.

Mechanical / Physical Properties

Compressive Strength	Ambient temperature: +30°C		(According to ASTM 1107-91)	
	1 day	3 days	7 days	28 days
	25 N/mm ²	35 N/mm ²	45 N/mm ²	65 N/mm ²

Flexural Strength	Ambient temperature: +30°C		(According to ASTM C 293-79)	
	7 days		28 days	
	5 N/mm ²		7 N/mm ²	

E-Modulus ~ 37'000 N/mm²

System Information

Application Details

Consumption *For 1 mm thickness per m²*
SikaGrout®-214: ~ 1.9 kg/l

Substrate Quality *Concrete, grout, stone:*
Surfaces must be sound, clean, free from ice, oils, grease, standing water and any loose or friable particles and any other surface contaminants.
The concrete "pull off" (tensile) strength should be > 1.0 MPa.

Steel, iron:
Clean, free from oil or grease, rust and scale etc.

Substrate Preparation The substrate should be prepared by suitable mechanical preparation techniques such as high pressure water jetting, breakers, blastcleaning, scabblers, etc.
The concrete substrates should be pre-soaked with clean water continuously for 2 - 6 hours to ensure a saturated surface dry condition throughout the operation.
Immediately before pouring remove *all* excess or standing water from within any formwork.

Application Conditions / Limitations

Substrate Temperature +5°C min/+40 °C max

Ambient Temperature +5°C min/+40 °C max

Application Instructions

Mixing	<p><i>SikaGrout®-214:</i></p> <p><i>For Flowable:</i> Water : grout powder = 1 : 6.25 to 1 : 7.14 parts by weight for a grout with good flow properties (3.5 - 4.0 l water per bag).</p> <p><i>For Pourable:</i> Water: grout powder = 1: 7.14 to 1: 8.33 parts by weight for a grout with good flow properties (3.0 - 3.5 l water per bag).</p>
Mixing Time	3 minutes minimum
Mixing Tools	<p>Mix grout powder mechanically in the correct ratio with water with low speed (max. 500 rpm) electric drill to avoid entraining too much air.</p> <p>Dependent on the desired consistency and flow properties, the mixing ratio can be adjusted. Don't use concrete tilting mixer.</p>
Application Method	<p>Pour grout immediately after mixing into the prepared openings. Ensure, that air displaced by the grout can easily escape, otherwise entrapped air will prevent full contact grouting. Wet porous substrates to saturated surface dry condition.</p> <p>When grouting base plates etc., ensure that a continuous and sufficient head of pressure is maintained to keep the grout flowing. To make optimum use of the products expansion properties, apply the grout as quickly as possible (within max. 15 minutes).</p>
Cleaning of Tools	Clean all tools and application equipment with water immediately after use. Hardened/cured material can only be mechanically removed.
Potlife	~ 20 minutes at +30°C
Notes on Application / Limitations	<ul style="list-style-type: none"> - Not to be used for patch repair works - Use only on clean, sound substrate - Keep exposed surface to the strict minimum
Curing Details	
Curing Treatment	Keep any visible, exposed grout surfaces as small as possible and protect from premature drying out by suitable measures (keep moist, cover with wet Hessian etc.).
Value Base	All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
Health and Safety Information	For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.
Legal Notes	The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

